



FULLY REFINED PARAFFIN WAX 60/62

<u>Property</u>	<u>Specification</u>	<u>Typical Result</u>	<u>Method</u>
Melting Point °C	60 - 62	60.7	ASTM D 87
Congearing Pt°C	60 – 62	60	ASTM D938
Viscosity cS @100°C	4 - 5	4.2	ASTM D445
Needle Penetration @ 25°C	14-17	15	ASTM D1321
Oil Content %	<0.5	0.3	ASTM D721
Colour Saybolt	>+25	+30	ASTM D156

Form and Packaging
onto 1000kg pallets.

PW 60/62 is as 5 kg slabs, five to a 25kg carton, consolidated

Availability

PW 60/62 is stocked in both Sydney and Melbourne.

Australian Wax Company Pty Ltd

ABN: 74 648 044 222

145 Osborne Avenue Clayton South 3169

Tel: 03 9546 4562